

باديكوت القطيه
Al-futtaim Bodycote

محص المواد
Materials Testing

ALFUTTAIM BODYCOTE TESTING (L.L.C.)
P.O. Box 34924 - DUBAI - U.A.E.

REPORT OF TESTS

Description	One Sample of Plywood		
Tested for	Procure IT Direct., Post Box No.112950, Dubai, U.A.E		
Lab Ref. No.	WR07-66451 (Page 1 of 1)	Request No.	WQ07-23480
Date Received	24.12.2007	Date Reported	29.12.2007

Client's reference : Requisition dated 24.12.2007
Sample reference : Plywood
AFBT sample No. : W07-023480/01

1.0 Introduction

Further to the test work instructions received from M/s. Procure IT Direct., Dubai, dated 24.12.2007, one sample of Strand board provided has been tested for the following by Al Futtaim Bodycote Testing I.L.C;

2.0 Bond Performance Test

Test Method: Test was carried out in general accordance with BS 6566: 1985

Rectangular specimens with dimensions of 6 inch x 6 inch were prepared from the supplied sample and submerged in boiling water under normal conditions for 72±3 hours. Then the specimens were immersed in water @ 15±5°C until cooled. After conditioning, the specimens were examined for any kind of bond failure.

Test	Observation
Bond Test	No sign of bond failure, glue failure or any other defects.



For and on behalf of Al Futtaim Bodycote Testing (L.L.C.)
Tested by: KSLN, Date tested: 26.12.2007-29.12.2007
Sampled by the client, certificate of sampling was not given.

This report shall only be reproduced in full. Approval of the testing laboratory is required for partial reproduction.
Samples will be retained for a period of one month only, unless otherwise requested.
The test results relate only to the samples tested.

